

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:

1. (currently amended): A rubber-modified styrene resin composition comprising 99.9 to 97 percent by weight of a rubber-modified styrene resin (E) and 0.1 to 3 percent by weight of a polyorganosiloxane-containing graft copolymer (D),

the polyorganosiloxane-containing graft copolymer (D) being a copolymer (a-1) that is prepared with a polyorganosiloxane (A), wherein the polyorganosiloxane (A) being produced by polymerizing 99.9 to 99.6 percent by weight of an organosiloxane and 0.1 to 0.4 percent by weight of a graft-linking agent,

wherein the copolymer (a-1) being prepared by polymerizing, in the presence of 86 to 94.99 parts by weight of the polyorganosiloxane (A), 0.01 to 5 parts by weight of a monomer (B), and then polymerizing the resulting polymer with 5 to 13.99 parts by weight of a vinyl monomer (C), to thereby provide a copolymer (a-1) consisting essentially of

86 to 94.99 parts by weight of polyorganosiloxane (A),

~~a polymer prepared by polymerizing, in the presence of the polyorganosiloxane (A), 0.01 to 5 parts by weight of a monomer (B), and~~

~~a polymer prepared by polymerizing, in the presence of the polyorganosiloxane (A) and the polymer of monomer (B), 5 to 13.99 parts by weight of a vinyl monomer (C); and~~

~~the polyorganosiloxane (A) being produced by polymerizing 99.9 to 99.6 percent by weight of an organosiloxane and 0.1 to 0.4 percent by weight of a graft linking agent, and~~
the monomer (B) consisting of 100 to 50 percent by weight of a polyfunctional monomer (b-1) having at least two polymerizable unsaturated bonds in its molecule and 0 to 50 percent by weight of another copolymerizable monomer (b-2);
wherein the sum of the compounds (A), (B), and (C) is 100 parts by weight per 100 parts of the graft copolymer.

2-3. (canceled).

4. (previously presented): The rubber-modified styrene resin composition according to claim 1, wherein the rubber-modified styrene resin comprises 99.9 to 99.1 percent by weight of the rubber-modified styrene resin (E) and 0.1 to 0.9 percent by weight of the polyorganosiloxane-containing graft copolymer (D).

5. (previously presented): The rubber-modified styrene resin composition according to claim 1, wherein each of the vinyl monomers (b-2) and (C) is at least one selected from the group of an aromatic vinyl monomer, a cyanovinyl monomer, a (meth)acrylate monomer, a vinyl monomer with a carboxyl group, and a maleimide monomer, the vinyl monomers (b-2) and (C) being used in preparing the polyorganosiloxane-containing graft copolymer (D).